



ExxonMobil™ AP3AW

Polypropylene Impact Copolymer

Product Description

An UV stabilized medium impact copolymer resin designed for automotive battery cases.

General			
Availability ¹	• Asia Pacific		
Features	• High Stiffness	• Medium Flow	• UV Resistant
	• Low Warpage	• Medium Impact Resistance	
Uses	• Automotive Applications	• Automotive Under the Hood	• Battery Cases
Appearance	• Natural Color		
Form(s)	• Pellets		
Processing Method	• Injection Molding		
Revision Date	• 07/01/2017		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10 g/10 min	10 g/10 min	ASTM D1238
Density	0.900 g/cm ³	0.900 g/cm ³	ExxonMobil Method

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (51 mm/min)	3930 psi	27.1 MPa	ASTM D638
Tensile Stress at Yield	3790 psi	26.1 MPa	ISO 527-2/50
Elongation at Yield (2.0 in/min (51 mm/min))	5.5 %	5.5 %	ASTM D638
Tensile Strain at Yield	5.7 %	5.7 %	ISO 527-2/50
Flexural Modulus - 1% Secant 0.051 in/min (1.3 mm/min)	204000 psi	1410 MPa	ASTM D790A
0.51 in/min (13 mm/min)	231000 psi	1590 MPa	ASTM D790B
Flexural Modulus (0.079 in/min (2.0 mm/min))	188000 psi	1300 MPa	ISO 178

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact 0°F (-18°C)	0.91 ft-lb/in	49 J/m	ASTM D256A
73°F (23°C)	2.2 ft-lb/in	120 J/m	
Notched Izod Impact Strength -40°F (-40°C)	2.5 ft-lb/in ²	5.3 kJ/m ²	ISO 180/1A
-4°F (-20°C)	2.7 ft-lb/in ²	5.6 kJ/m ²	
73°F (23°C)	6.6 ft-lb/in ²	14 kJ/m ²	
Charpy Notched Impact Strength -22°F (-30°C)	2.0 ft-lb/in ²	4.2 kJ/m ²	ISO 179/1eA
-4°F (-20°C)	2.1 ft-lb/in ²	4.4 kJ/m ²	
32°F (0°C)	3.1 ft-lb/in ²	6.5 kJ/m ²	
73°F (23°C)	5.6 ft-lb/in ²	12 kJ/m ²	
Gardner Impact -20°F (-29°C), 0.125 in (3.18 mm), Geometry GC	156 in-lb	17.6 J	ASTM D5420

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Heat Deflection Temperature (1.80 MPa)	132 °F	55.8 °C	ISO 75-2/49 °C
Heat Deflection Temperature (0.45 MPa)	197 °F	91.7 °C	ISO 75-2/49 °C
Deflection Temperature Under Load (DTUL) at 66psi – Unannealed	210 °F	99.0 °C	ASTM D6449 °C
DTUL at 66psi – Annealed	239 °F	115 °C	ASTM D6449 °C

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Rockwell Hardness	94	94	ASTM D785

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance please contact our sales representative

©2020-2021. Union Petrochemical. The user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. Union Petrochemical does not guarantee the typical (or other non-specification) values. Typical values only represent the values one would expect if the properties were tested in our laboratories with our test methods on the specified date. Some product properties are not frequently measured, and accordingly typical values may not be based upon a statistically relevant number of tests. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no warranty against patent infringement, not any endorsement of any product or process, and we expressly disclaim any contrary implication.