



ExxonMobil™ PP1304E5

Polypropylene Homopolymer

Product Description

A homopolymer resin designed for injection molding applications requiring excellent flow and good mechanical properties. It is designed for caps and closures, general purpose applications such as toys, electric appliances, packaging and thin walled parts.

Key Features

- Medium transparency
- High stiffness
- High surface hardness
- High heat
- Medium impact strength

General

Availability ¹	• Africa & Middle East	• Asia Pacific	
Uses	• Consumer Applications	• Furniture	• Packaging
	• Crates	• Industrial Applications	• Tool/Tote Box
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Compounding	• Injection Molding	
Revision Date	• 05/01/2017		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11 g/10 min	11 g/10 min	ASTM D1238
Density	0.900 g/cm ³	0.900 g/cm ³	ExxonMobil Method

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at Yield	4790 psi	33.0 MPa	ISO 527-2/1A/50
Tensile Strain at Yield	9.0 %	9.0 %	ISO 527-2/1A/50
Tensile Modulus	206000 psi	1420 MPa	ISO 527-2/1A/1
Flexural Modulus (0.079 in/min (2.0 mm/min))	193000 psi	1330 MPa	ISO 178

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Charpy Notched Impact Strength (73°F (23°C))	1.6 ft-lb/in ²	3.3 kJ/m ²	ISO 179/1eA

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Peak Melting Temperature	318 °F	159 °C	ASTM D3418
Heat Deflection Temperature (0.45 MPa)	177 °F	79.0 °C	ISO 75-2/B

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Shore Hardness (Shore D, 15 sec)	70	70	ISO 868

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance please contact our sales representative

©2020-2021. Union Petrochemical. The user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. Union Petrochemical does not guarantee the typical (or other non-specification) values. Typical values only represent the values one would expect if the properties were tested in our laboratories with our test methods on the specified date. Some product properties are not frequently measured, and accordingly typical values may not be based upon a statistically relevant number of tests. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no warranty against patent infringement, not any endorsement of any product or process, and we expressly disclaim any contrary implication.