



ExxonMobil™ PP5722E1

Polypropylene Homopolymer

Product Description

A medium flow homopolymer resin designed for mono-oriented products like stretched tapes and monofilament.

General		
Availability ¹	• Asia Pacific	
Features	• Good Gauge Control • Good Processability	• Low Water Carryover • Medium Flow
Uses	• Fabrics • Rope	• Tape • Yarn
Appearance	• Natural Color	
Form(s)	• Pellets	
Processing Method	• Extrusion	
Revision Date	• 03/01/2010	

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0 g/10 min	4.0 g/10 min	ASTM D1238
Density	0.900 g/cm ³	0.900 g/cm ³	ExxonMobil Method

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (51 mm/min)	5090 psi	35.1 MPa	ASTM D638
Elongation at Yield (2.0 in/min (51 mm/min))	9.8 %	9.8 %	ASTM D638
Flexural Modulus - 1% Secant 0.051 in/min (1.3 mm/min) 0.51 in/min (13 mm/min)	215000 psi 246000 psi	1480 MPa 1700 MPa	ASTM D790A ASTM D790B

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact (73°F (23°C))	0.74 ft-lb/in	40 J/m	ASTM D256A
Gardner Impact 73°F (23°C), 0.125 in (3.18 mm), Geometry GC	26.9 in-lb	3.04 J	ASTM D5420

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 66psi – Unannealed	200 °F	93.5 °C	ASTM D648

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Rockwell Hardness	106	106	ASTM D785

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance please contact our sales representative

©2020-2021. Union Petrochemical. The user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. Union Petrochemical does not guarantee the typical (or other non-specification) values. Typical values only represent the values one would expect if the properties were tested in our laboratories with our test methods on the specified date. Some product properties are not frequently measured, and accordingly typical values may not be based upon a statistically relevant number of tests. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no warranty against patent infringement, not any endorsement of any product or process, and we expressly disclaim any contrary implication.