



# Vistamaxx™ 3980FL

## Performance Polymer

### Product Description

- Vistamaxx 3980FL is primarily composed of isotactic propylene repeat units with random ethylene distribution. The 'FL' designates this product passes test for film appearance with regard to gels, as needed for performance film applications ('A' rating).
- Vistamaxx polymers have a wide temperature processing window. A good starting point for temperatures is 10°C above the highest melting point. This material does not require drying and can be compounded or used in a dry blend. Use conventional processing knowledge to ensure mixing of the materials.

### Key Features

- Suitable for a wide range of cast and blown film, molding and various polymer modification and compounding applications.
- Can be blended with PP, PE and other polyolefins to reduce stress whitening and improve impact properties.
- Excellent adhesion to conventional and metallocene PP and PE for exceptional extrusion coating, lamination and tie layer performance.
- Very low seal initiation temperature combined with high seal strength when used as a sealing layer of co-extruded structures.
- Good optical properties.
- Good chemical resistance to aqueous systems and non-hydrocarbon based fluids.
- May be used in food contact applications (see FDA and EU notes).
- RoHS compliant.

### General

Availability <sup>1</sup>	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Applications	• Blown Film	• Compounding	• Polymer Modification
	• Cast Film	• Molding	
Uses	• Compounding	• Film	• Packaging
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Revision Date	• 01/01/2017		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Density <sup>2</sup>	0.879 g/cm <sup>3</sup>	0.879 g/cm <sup>3</sup>	ASTM D1505
Melt Index <sup>2</sup> (190°C/2.16 kg)	3.6 g/10 min	3.6 g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) <sup>2</sup> (230°C/2.16 kg)	8 g/10 min	8 g/10 min	ExxonMobil Method
Ethylene Content	9 wt%	9 wt%	ExxonMobil Method

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Durometer Hardness (Shore D)	34	34	ASTM D2240

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100%	953 psi	6.57 MPa	ASTM D638
Tensile Stress at 300%	1030 psi	7.10 MPa	ASTM D638
Tensile Stress at Yield	1150 psi	7.92 MPa	ASTM D638
Tensile Stress at Break	> 2800 psi	> 19.3 MPa	ASTM D638
Tensile Set	73 %	73 %	ExxonMobil Method
Elongation at Yield	27 %	27 %	ASTM D638
Elongation at Break	> 800 %	> 800 %	ASTM D638
Flexural Modulus - 1% Secant	17000 psi	117 MPa	ASTM D790

Elastomers	Typical Value (English)	Typical Value (SI)	Test Based On
Tear Strength (Die C)	476 lbf/in	83.4 kN/m	ASTM D624

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	171 °F	77.3 °C	ExxonMobil Method

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

<sup>2</sup> Property specified in conventional unit of measure.

For additional technical, sales and order assistance please contact our sales representative

©2020-2021. Union Petrochemical. The user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. Union Petrochemical does not guarantee the typical (or other non-specification) values. Typical values only represent the values one would expect if the properties were tested in our laboratories with our test methods on the specified date. Some product properties are not frequently measured, and accordingly typical values may not be based upon a statistically relevant number of tests. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no warranty against patent infringement, not any endorsement of any product or process, and we expressly disclaim any contrary implication.